FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
★ ★ ★ ★ ★
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16/

1. TESTING OF COARSE AGGREGATES (40 mm): **Date: 02-07-2015**

Sub: Testing of Coarse Aggregates.
{Project*: Improvements to Roads and Drains at Srinivasapura Village in Ward No.05, Byatarayanapura Sub-Division}
Ref. : Letter No. Testing/BUB/2015-16, dated 27-06-2015
Sample supplied to lab by: Sri.S.K.Keshavamurty, Contractor, Bangalore.
Report Required for : Assistant Executive Engineer, Byatarayanapura Sub-Division, BBMP, Bangalore

Table - 1.1 : SIEVE ANALYSIS :

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2002) % Passing	
	40 mm Sample	*Single size*	*Graded*
40mm	96.70	85-100	95 – 100
20mm	67.20	0 -20	30- 70
10mm	28.00	0 -5	10- 35
4.75mm	Nil	------	0 - 5

TABLE 1 2 :

SL No	Test conducted	Sample No	Results	Requirements as per IS:383-1970 & Test Conforms to IS 2386(Part I to IV) – 1963 (Reaffirmed on 2002)
1.	Flakiness Index	As above	16.50 %	Not to exceed 25 %
2.	Crushing value	----,,----	25.30%	Not to exceed 45 % for concrete other than for wearing surfaces and 30% for concrete for wearing surfaces

*As Furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Compus
BANGALORE UNIVERSITY
Bangalore-560 056.

Assistant Executive Engineer
Byatarayanapura Sub Division
B.B.M.P. Bangalore

Dr. MANJESH .L
ME (Civil Engg). Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail. manjeshl@yahoo.co.in

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
★ ★ ★ ★ ★
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16 **Date: 02-07-2015**

1. TEST REPORT ON REINFORCEMENT STEEL :

Sub: Testing of Reinforcement Steel of diameter 12mm.
{Project*: Improvements to Roads and Drains at Srinivasapura Village in Ward No.05, Byatarayanapura Sub-Division}

Ref. : Letter No. Testing/BUB/2015-16, dated 27-06-2015

Sample supplied to lab by: Sri.S.K.Keshavamurty, Contractor, Bangalore.

Report Required for : Assistant Executive Engineer, Byatarayanapura Sub-Division, BBMP, Bangalore

TABLE – 1

SL No	Details	For 12mm	
		Test Results	Min Req as per IS 1786-2008
01	Observed diameter of bar	**12.0mm**	12.0mm
02	Observed Wt/m Length **Kg/m**	**0.891**	0.834
03	Proof stress/Yield stress, fy , **N/mm^2**	**560.0**	500.0
04	Bend/ Re bend Test	**Ok**	---
05	Percentage of Elongation, %	**20.50**	12.00
06	Ultimate Tensile Strength **N/mm^2**	**618.0**	545.0

*As furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Campus
BANGALORE UNIVERSITY
Bangalore-560 056.

Dr. MANJESH .L
ME (Civil Engg), Ph D MISTE MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail: manjeshl@yahoo.com

Assistant Executive Engineer
Byatarayanapura Sub Division
B.B.M.P. Bangalore

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
★ ★ ★ ★ ★
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16/

1. TESTING OF FINE AGGREGATES: **Date: 02-07-2015**

Sub: Testing of Fine Aggregates.
{Project*: Improvements to Roads and Drains at Srinivasapura Village in Ward No.05, Byatarayanapura Sub-Division}

Ref. : Letter No. Testing/BUB/2015-16, dated 27-06-2015

Sample supplied to lab by: Sri.S.K.Keshavamurty, Contractor, Bangalore.

Report Required for : Assistant Executive Engineer, Byatarayanapura Sub-Division, BBMP, Bangalore

TABLE - 1.1 : SIEVE ANALYSIS :

IS Sieve Size, mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -III	
04.75	97.00	90-100	90-100	90-100	The Sample Conforms to Grading **Zone-II**
02.36	85.00	60-95	75-100	85-100	
01.18	74.10	30-70	55-90	75-100	
600. mic	46.00	15-34	35-59	60-79	
300.mic	17.00	5-20	8-30	12-40	
150.mic	3.10	0-10	0-10	0-10	

TABLE 1.2 ;

Sl No	Test Conducted	Sample	Results	Requirements as Per IS. Specification IS :383-1970 (Reaffirmed 2002)
1	Silt Content	001	1.44 %	Not more than 8%
2.	Specific Gravity	----	2.60	-------

*As Furnished by Client.

The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Campus
BANGALORE UNIVERSITY
Bangalore-560 056.

Assistant Executive Engineer
Byatarayanapura Sub Division
B.B.M.P. Bangalore

Dr. MANJESH .L
ME (Civil Engg .). Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail: manjeshl@yahoo.com

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

JNANA BHARATHI
BANGALORE - 560 056

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
Accredited by NAAC

BUB/CTE/2015-16/

1. TEST REPORT ON CEMENT:

Date: 06-07-2015

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Improvements to Roads and Drains at Srinivasapura Village in Ward No.05, Byatarayanapura Sub-Division}
Ref. : Letter No. Testing/BUB/2015-16, dated 27-06-2015
Sample supplied to lab by: Sri.S.K.Keshavamurty, Contractor, Bangalore.
Report Required for : Assistant Executive Engineer, Byatarayanapura Sub-Division, BBMP, Bangalore

PHYSICAL TESTS ON CEMENT

Brand* : Birla
Grade * : 53
Type * : OPC
Date : 28-06-2015 to 05-07-2015

SL No	Name of Test	Results	Requirements as per
		Cement Sample	IS 12269-1987
1	Initial setting time	**160 min**	Shall not be less than 30 min
2	Final setting time	**255 min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**2.60 %**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**1.80 mm**	Shall not be more than 10 mm
5	Compressive strength c) 3 days (average of three results) d) 7 days (average of three results)	**29.70 N/ Sq mm** **41.20 N/Sq mm**	Shall not be less than 27 N/Sqmm Shall not be less than 37N/Sqmm

*As Furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Campus
BANGALORE UNIVERSITY
Bangalore-560 056.

Byatarayanapura Sub Division
B.B.M.P. Bangalore

6/7/2015
Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail: manjeshl@yahoo.com

AE-05

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16/

DATE: 21-07-2015

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (07 days Compressive Strength)
{Project*: Improvements to Roads and Drains at Srinivasapura Village in Ward No.05, Byatarayanapura Sub-Division}
Ref. : Letter No. Testing/BUB/2015-16, dated 20-07-2015
Sample supplied to lab by: Sri.S.K.Keshavamurty, Contractor, Bangalore.
Report Required for : Assistant Executive Engineer, Byatarayanapura Sub-Division, BBMP, Bangalore

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1 :

Sl No	Location/ Identification *	Date of Casting*	Date of Testing	Age in Days	C/S Area in Mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	13-07-15	20-07-15	07	22500	400	17.77	**17.55**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	400	17.77	

*As Furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Campus
BANGALORE UNIVERSITY
Bangalore-560 056.

Assistant Executive Engineer
Byatarayanapura Sub Division
B.B.M.P. Bangalore

Dr. MANJESH .L
ME (Civil Engg.) Ph.D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e-mail: manjeshl@yahoo.com

ಸಹಾಯಕ ಕಾರ್ಯ ಪಾಲಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16/

Date: 01-07-2015

TEST REPORT ON WET MIX MACADAM MIX

(GRADATION TEST)

Sub: To conduct Gradation test on Wet Mix Macadam (WMM) Mix.
{Project*: Improvements to Roads and Drains at Srinivasapura Village in Ward No.05, Byatarayanapura Sub-Division}

Ref. : Letter No. Testing/BUB/2015-16, dated 27-06-2015

Sample supplied to lab by: Sri.S.K.Keshavamurty, Contractor, Bangalore.

Report Required for : Assistant Executive Engineer, Byatarayanapura Sub-Division, BBMP, Bangalore

TEST RESULTS

1. Gradation Test:

TABLE 1.1

Sieve Size mm	Percent by Weight passing the Sieve from the sample supplied (Obtained Gradation)	Specified Limits as per MoRTH Specifications, IV Revision-2001
53.00	**100.00**	100
45.00	**96.40**	95-100
26.50	**---**	-
22.40	**76.00**	60-80
11.20	**42.10**	40-60
4.75	**32.00**	25-40
2.36	**24.20**	15-30
0.600	**17.30**	8-22
0.075	**4.80**	0-8

*As Furnished by Client

The Results relate only to the items tested

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Campus
BANGALORE UNIVERSITY
Bangalore-560 056.

Assistant Executive Engineer
Byatarayanapura Sub Division
B.B.M.P. Bangalore

Dr. MANJESH .L
ME (Civil Engg.) Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail: manjeshl@yahoo.com

AE-05

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16/ **Date: 03-07-2015**

TEST REPORT ON WET MIX MACADAM MIX

(GRADATION TEST)

Sub: To conduct Gradation test on Wet Mix Macadam (WMM) Mix.
{Project*: Improvements to Roads and Drains at Srinivasapura Village in Ward No.05, Byatarayanapura Sub-Division}

Ref. : Letter No. Testing/BUB/2015-16, dated 01-07-2015

Sample supplied to lab by: Sri.S.K.Keshavamurty, Contractor, Bangalore.

Report Required for : Assistant Executive Engineer, Byatarayanapura Sub-Division, BBMP, Bangalore

TEST RESULTS

1. Gradation Test:

TABLE 1.1

Sieve Size mm	Percent by Weight passing the Sieve from the sample supplied (Obtained Gradation)	Specified Limits as per MoRTH Specifications, IV Revision-2001
53.00	**100.00**	100
45.00	**97.30**	95-100
26.50	**---**	-
22.40	**74.10**	60-80
11.20	**44.00**	40-60
4.75	**36.00**	25-40
2.36	**25.10**	15-30
0.600	**18.30**	8-22
0.075	**5.10**	0-8

*As Furnished by Client

The Results relate only to the items tested

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Compus
BANGALORE UNIVERSITY
Bangalore-560 056.

Dr. MANJESH .L
ME (Civil Engg.), Ph.D, MISTE, MIRC
Associate Professor
Department of Civil Engineering
Bangalore University, Jnanabharathi Campus
BANGALORE- 560 056
e-mail: manjeshl@gmail.com

Assistant Executive Engineer
Byatarayanapura Sub Division
B.B.M.P. Bangalore

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
★ ★ ★ ★ ★
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16/ **Date: 22-07-2015**

TEST REPORT ON BITUMINOUS MIXES
(BITUMEN EXTRACTION TEST & GRADATION TEST)

Sub: Testing of Bitumen Premix Sample (Semi Dense Bituminous Concrete-SDBC).
{Project*: Improvements to Roads and Drains at Srinivasapura Village in Ward No.05, Byatarayanapura Sub-Division}

Ref. : Letter No. Testing/BUB/2015-16, dated 20-07-2015

Sample supplied to lab by: Sri.S.K.Keshavamurty, Contractor, Bangalore.

Report Required for : Assistant Executive Engineer, Byatarayanapura Sub-Division, BBMP, Bangalore

TEST RESULTS:

1. The bitumen content obtained after subjecting the sample for Bitumen Extraction test = **5.07%**
2. **Gradation Test** :

Sieve Size, mm	Percent by Weight passing the Sieve from the sample supplied (Obtained Gradation)	Gradation requirement as per Table 500-15 of MORTH Specifications-2001 (Grading – 2)
13.2	**100**	100
9.5	**97.00**	90—100
4.75	**45.10**	35—51
2.36	**36.70**	24—39
1.18	**23.00**	15—30
0.3	**16.20**	09—19
0.075	**4.60**	03—08

* As furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Compus
BANGALORE UNIVERSITY
Bangalore-560 056.

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

Assistant Executive Engineer
Byatarayanapura Sub Division,
B.B.M.P. Bangalore

Dr. MANJESH .L
ME (Civil Engg.), Ph.D, MISTE, MIRC
Associate Professor
Department of Civil Engineering
Bangalore University, Jnanabharathi, ...
BANGALORE- 560 056
e-mail: manjeshl@yahoo.com